

MATERIAL PROPERTIES

Pultex® Fiber Reinforced Polymer Structural Profiles Rectangular Tubes, Channels, Angles, Square Tubes, Round Tubes

*Includes all angles except 102mm x 6mm, 102mm x 10mm, 152mm x 10mm and 152mm x 13mm
which are **SuperStructurals**.
Please consult the Pultex® Fiber Reinforced Polymer **SuperStructural** Profiles Angles Material Properties*

Metric Version

1500 Series - Thermoset Polyester – Olive Green
1525 Series - Thermoset Polyester Class 1 FR – Slate Gray (Dark Gray)
1625 Series - Thermoset Vinyl Ester Class 1 FR – Beige

The following data was derived from ASTM coupon and full section testing. The results are average values based on random sampling and testing of production lots. Composite materials are not homogeneous; and therefore, the location of the coupon extraction can cause variances in the coupon test results. Creative Pultrusions publishes an average value of random samples from production lots.

Property (coupon values)	ASTM Test	Units	1500/1525 Series	1625 Series
Mechanical				
Tensile Strength (LW)	D638	MPa	226.9	257.8
Tensile Strength (CW)	D638	MPa	51.6	55.0
Tensile Modulus (LW)	D638	GPa	17.2	20.6
Tensile Modulus (CW)	D638	GPa	5.5	6.9
Compressive Strength (LW)	D695	MPa	226.9	257.8
Compressive Strength (CW)	D695	MPa	113.4	137.5
Compressive Modulus (LW)	D695	GPa	20.6	20.6
Compressive Modulus (CW)	D695	GPa	6.9	8.2
Flexural Strength (LW)	D790	MPa	226.9	257.8
Flexural Strength (CW)	D790	MPa	75.6	85.9
Flexural Modulus (LW)	D790	GPa	11.0	13.7
Flexural Modulus (CW)	D790	GPa	5.5	6.9
Modulus of Elasticity (Channels)	Full Section ²	GPa	19.2-22.0	19.2-22.0
(Square and Rectangular Tubes)	Full Section ²	GPa	19.2	19.2
Shear Modulus	Full Section ²	GPa	22.0	22.0
Interlaminar Shear (LW) ³	D2344	MPa	2.9	2.9
Shear Strength By Punch (PF)	D732	MPa	31.0	31.0
Notched Izod Impact (LW)	D256	J/m	37.8	41.2
Notched Izod Impact (CW)	D256	J/m	1494.6	1601.4
Maximum Bearing Strength (LW)	D953	MPa	213.5	266.9
Maximum Bearing Strength (CW)	D953	MPa	206.2	206.2
Poisson's Ratio (LW)	D3039	mm/mm	123.7	123.7
Poisson's Ratio (CW)	D3039	mm/mm	0.35	0.35
In-Plane Shear (LW)	Modified D2344 ⁴	MPa	0.15	0.15
			48.3	48.3

LW = lengthwise

CW = crosswise

PF = perpendicular to laminate face

Additional properties located on page back



CREATIVE PULTRUSIONS, INC.

214 Industrial Lane ■ Alum Bank, PA ■ 15521

814-839-4186 ■ Fax: 814-839-4276

Web site: <http://www.creativepultrusions.com> ■ E-mail: crpul@pultrude.com

Flowgrip® and Pultex® are registered trademarks of Creative Pultrusions, Inc. Creative Pultrusions™, Shaping the Future™, Superstud™, Superstud™/Nuts!, Superstik™, SUPURTUF™, Superplank™, Superdeck™, Supergrate™, Tuf-dek™, SuperLoc™, SuperWale™, SuperCap™, SuperRod™, Pultrusion Dynamics™, DYNAPUL™, Pulshaping™, TOPSCAN™ and TOPDIE™ are trademarks of Creative Pultrusions, Inc.

MATERIAL PROPERTIES

Pultex[®] Fiber Reinforced Polymer Structural Profiles Rectangular Tubes, Channels, Angles, Square Tubes, Round Tubes Metric Version

*Includes all angles except 102mm x 6mm, 102mm x 10mm, 152mm x 10mm and 152mm x 13mm
which are **SuperStructurals**.*

*Please consult the Pultex[®] Fiber Reinforced Polymer **SuperStructural** Profiles Angles Material Properties*

(cont'd)

Property (coupon values)	ASTM Test	Units	1500/1525 Series	1625 Series
Physical				
Barcol Hardness ¹	D2583		45	45
Water Absorption	D570	% Max	0.6	0.6
Density	D792	Mg/m ³	1.66-1.93	1.66-1.93
Specific Gravity	D792		1.66-1.93	1.66-1.93
Coefficient of Thermal Expansion (LW)	D696	10 ⁻⁶ K ⁻¹	8	8
Thermal Conductivity (PF)	C177	W/mK	0.58	0.58
Electrical				
Arc Resistance (LW)	D495	seconds	120	120
Dielectric Strength (LW)	D149	kV/mm	1.58	1.58
Dielectric Strength (PF)	D149	kV/mm	7.9	7.9
Dielectric Constant (PF)	D150	@60Hz	5.2	5.2

¹ Pultex[®] uses a synthetic surface veil that reduces the Barcol Hardness, but does not reflect lack of cure.

² Full section testing based on a 3-point bend with simply supported end conditions (Reference The New and Improved Pultex[®] Pultrusion Global Design Manual, Appendix B, for details).

³ Tested on a 3:1, span to depth ratio.

⁴ Follow ASTM D2344, but rotate coupon 90° (cut section of coupon length faces up).

⁵ In-plane Shear (CW) values for square tubes and rectangular tubes = 17.2 MPa; angles = 26.2 MPa

Property	ASTM Test	Value	
		1525	1625
Flammability Classification	UL94	(VO)	(VO)
Tunnel Test	ASTM E-84	25 Max	25 Max
Flammability Extinguishing	ASTM D635	Self extinguishing	Self extinguishing
NBS Smoke Chamber	ASTM E662	650	650

Creative Pultrusions, Inc. believes the information put forth in this property sheet to be as accurate and reliable as of the date of publication. However, we assume no obligation or liability which may arise as a result of its use. While Creative Pultrusions, Inc. has no knowledge that the information put forth infringes any valid patent, it assumes no responsibility with respect thereto and each user must satisfy oneself that one's intended application process or product infringes no patent.

"No portion of this Material Properties Sheet may be reproduced in any form without the prior written consent of Creative Pultrusions, Inc."

Copyright © 2007 by

Creative Pultrusions, Inc.

All Rights Reserved